MEDIDERM® 3701

Medical Adhesive Laminate

Description

Polyurethane Film coated on one side with a pressure-sensitive acrylic adhesive, laminated to a silicone release liner

Characteristics


- Conformable
- Medium MVT Laminate

Properties

| Tests Performed Adhesive Coat Weight (g/m²) | Typical Values 26 |
|--|--------------------------|
| Adhesion to Stainless Steel (g/inch) | 670 |
| Peel from Release Liner (g/2 inch) | 30 |
| Polyken Tack (g/cm²) | 211 |
| MVTR (g/m²/day) | 875 |

Typical values are intended to used as a guide and are not intended for specification purposes

Limited Warranty Statement on Reverse



Ordering Information

Width Maximum 43 inches
Diameter Maximum 20 inches
Length Maximum 1,000 feet

Safety Testing Consistent with intended application

Storage Temperature 50-80°F; Humidity 40-60%



Limited Warranty and Conditions — Please Read Carefully Mylan believes the information in this publication is an accurate description of the typical; characteristics and/or uses of the product(s). It is the purchaser's responsibility to thoroughly test the product in the purchaser's specific application to determine its performance, efficacy and safety, especially in light of any third party intellectual property rights. Suggestions of uses should not be taken as inducements to infringe any particular patent or other protected proprietary rights. Unless Mylan provides you with a separate specific written warranty of fitness for a particular use, Mylan's sole warranty is that the product(s) as supplied, will meet Mylan's then current sales specification. MYLAN SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WAR-RANTY, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND OF FITNESS FOR USE. Your exclusive remedy and Mylan's sole liabil-

ity for breach of warranty is limited to refund of the purchase price or replacement of any Mylan product shown to be other than as warranted, and

Mylan expressly disclaims any liability for incidental or consequential damages. Applicable test methods and product specifications available upon request.